Premium
Exterior Latex Flat Paint
GL61XX

DESCRIPTION

GLIDDEN™ exterior flat paint is ideal for all exterior siding, brick, masonry and stucco. Specially formulated with 100% acrylic latex to protect against UV rays, color fading and severe weather conditions. Provides a mildew resistant coating that can be applied in low temperatures (above 35ºF), allowing you to extend the painting season.

FEATURES

- Exceptionally durable flat finish
- Weather resistant against blistering, peeling and flaking
- Fade and chalk resistant
- Low temperature application (above 35ºF)
- Provides mildew resistant coating
- Quick drying and recoat
- Easy application
- Low Odor
- Soap and water cleanup

COMPOSITION

- 100% Acrylic Resin
- Titanium Dioxide and Extender Pigments
- Not manufactured with lead or mercury containing materials.

SPECIFICATION DATA

Color:
White & custom colors
Tint appropriate base with universal colorants

Finish: Flat
Sheen - 10 units maximum @ 85º
Gloss - 5 units maximum @ 60º

Clean-up Solvent:
Soap & water

Density:
11.31 lbs/gal (1.35 kg/L)

VOC:
50 g/L (0.42 lbs/gal) maximum

Solids:
Volume - 36% +/- 1%
Weight - 52% +/- 1%

Practical Coverage:
Apply at 300-400 sq ft/gal (7-10 m^2/L). Actual coverage may vary depending on substrate and application method.

Recommended Film Thickness:
4.0 - 5.3 mils wet
1.4 - 1.9 mils dry

Flash Point:
None

Dry Time:
77°F (25°C) & 50% RH
To touch - 1 hour
To recoat - 4 hours
35°F (2°C)
To touch - 3-6 hours
To recoat - 24 hours

Shelf Life:
1 year minimum - unopened

9 FINISHES PAINTING (09900)

Read Label and Material Safety Data Sheet Prior to Use. See other cautions on last page. DSF1-0690

PREPARING SURFACES FOR A PROFESSIONAL FINISH

PREPARING PAINTED SURFACES

Spackle holes or cracks. Lightly sand glossy areas. Make sure all areas are clean, sound and free of flaking paint or any substances such as oil, grease, dirt or mildew. Spot prime bare areas with an exterior primer. Prime woods prone to cracking such as yellow pine or T-1-11 plywood siding with an exterior acrylic primer.

IT'S TIME TO PRIME - PREPARING UNPAINTED SURFACES

WOOD - Sand lightly to a smooth surface. Prime woods prone to cracking such as yellow pine or T-1-11 plywood siding with an exterior primer. Always prime tannin containing woods such as redwood or cedar with an exterior primer.

CONCRETE, PLASTER AND MASONRY - Cure for 30 days before painting. "Slick poured" or pre-cast concrete needs chemical cleaning or a light sandblasting. Thoroughly rinse with water and allow to fully dry. Remove loose aggregate and prime with an exterior primer. For concrete block, fill with a latex block filler.

STEEL, GALVANIZED METAL AND ALUMINUM - Clean off oils, then prime with an appropriate metal primer.

WEATHERED ALUMINUM AND VINYL SIDING - Remove dirt and chalk. Prime with this product. If chalk remains after cleaning, prime with an exterior primer. When repainting vinyl siding, never use a color darker than the original color. Using a color darker than the original siding color will result in warping of the vinyl siding.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear an NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

DIRECTIONS FOR USE

QUALITY TOOLS FOR A QUALITY JOB

Use a quality 1/2" or larger nap roller, nylon or polyester brush, paint pad, or airless sprayer.

LET'S GET PAINTING

Mix thoroughly • Apply at package consistency • Thin only when using an airless sprayer if necessary using 1/2 pint water per gallon • For airless spray application, use .015-.017" tip. Adjust pressure as needed• Make sure the air, paint and the surface you are painting are above 35º F • Do not paint if rain, snow, heavy dew or lower temperatures are expected within 48 hours of painting • Dampen roller slightly with water • Dries to touch in one hour and to recoat in four hours at 77°F (25°C) • Dry to touch in 3-6 hours and to recoat in 24 hours at 35°F (2°C) • Apply at 300-400 sq ft/gal. (7-10 m^2/L) • Actual coverage may vary depending on surface texture, porosity and application method • Paint all trim including, windows, shutters & door frames first • Certain colors may require more than one coat for complete hide • Begin at highest point, working towards the ground.

LET'S CLEAN UP

Clean hands and tools with warm, soapy water • Clean spills right away with a damp cloth • After 30 days or paint has fully cured, areas may be washed with a non-abrasive, mild detergent.

PRECAUTIONS

WARNING! CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. MAY BE HARMFUL IF SWALLOWED. CONTAINS CRYSTALLINE SILICA WHICH CAN CAUSE LUNG CANCER AND OTHER LUNG DAMAGE IF INHALED. WHEN TINTED, CONTAINS ETHYLENE GLYCOL AND DIETHYLENE GLYCOL. ETHYLENE GLYCOL CAN CAUSE SEVERE KIDNEY DAMAGE WHEN INGESTED AND HAS BEEN SHOWN TO CAUSE BIRTH DEFECTS IN LABORATORY ANIMALS. DIETHYLENE GLYCOL MAY CAUSE CENTRAL NERVOUS SYSTEM EFFECTS AND LIVER, KIDNEY DAMAGE. USE ONLY WITH ADEQUATE VENTILATION! KEEP OUT OF THE REACH OF CHILDREN. For emergency information call (800) 545-2643. For additional safety information, refer to the Material Safety Data Sheet for this product. If sanding, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. Avoid contact with eyes and skin. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID**: For skin contact, wash thoroughly with soap and water. If any product remains, gently rub with petroleum jelly, vegetable or mineral/baby oil then wash again with soap and water. Repeat as needed. Remove contaminated clothing. For eye contact, flush immediately with plenty of water for at least 15 minutes. **Get medical attention**. If swallowed, **get medical attention immediately**. If inhalation causes discomfort, remove to fresh air. If discomfort persists or breathing difficulty occurs, get medical attention. **KEEP FROM FREEZING.**

DS392-1105

SHIPPING

FREIGHT CLASSIFICATION:
Paint, Freezable

PACKAGING:
4 quart (0.9168 L)
1 gallon (3.785 L)
5 gallons (18.925 L)

FLASH POINT:
None

AkzoNobel
Akzo Nobel Paints LLC, Strongsville, Ohio 44136

Glidden
1-800-GLIDDEN • www.glidden.com

LIMITATION OF LIABILITY To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.